

TECHNICAL DATA

Scapa 2702

PVC Electrical Adhesive Tape

DESCRIPTION

Scapa 2702 is a 0.13mm premium quality, electrical self-extinguishing soft PVC tape that uses an aggressive pressure sensitive rubber-based adhesive system. It has been designed for use where a recognised specification or international standard is required and where environmental safety is a concern.

APPLICATIONS

- Primary electrical insulation
- Protection for low and medium voltage cable splices
- Colour coding
- Industrial applications
- Used for electrical cables wrapping in automotive application
- Hand application

PRODUCT BENEFITS

- Good resistance to abrasion, corrosion and moisture
- High dielectric strength and good mechanical protection
- Outstanding conformability
- Environmentally friendly technology
- Approved by IMQ, VDE, ÖVE
- Conforms to BS3924
- Conforms to European Directive 2000/53 EC (lead, chromium VI, mercury, cadmium free)
- Service temperature: 0°C to + 90°C

Issue: 4 Date: 25/01/2005 Page 1 of 2 2702.doc

www.scapa.com

TECHNICAL PROPERTIES

	Unit	Nominal Value	Test Method
Thickness	mm	0.13	CEI EN 60454
Tensile Strength	N/cm	25	CEI EN 60454
Elongation at Break	%	180	CEI EN 60454
Adhesion to Steel	N/cm	1.8	CEI EN 60454
Adhesion to Backing	N/cm	1.8	CEI EN 60454
Dielectric Strength	KV/mm	40	CEI EN 60454
Flammability		Self extinguishing	CEI EN 60454

STANDARD PRESENTATION

Roll length : 10, 20, 25 and 33 metres
Roll width : 12, 15, 19 and 25mm

Core : 32 mm Scapa branded cardboard core

Packaging : Cellowrapped with Scapa label and bar code

■ Colours : Black, White, Grey, Red, Blue, Yellow, Dark green, Light Green, Brown, Orange,

Violet, Transparent, Yellow/green

RECOMMENDATIONS

Rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. The storage temperature should be between +10°c and +25°c. Use within 24 months of receipt.

The tape should be applied with sufficient tension to ensure an optimum bonding and a minimum of two layers with a half overlap. The final layer should be wrapped with a lower tension to prevent flagging effects.

Surfaces should be clean, dry and free of dust, grease, oil or other contaminants.

Issue: 4 Date: 25/01/2005 Page 2 of 2 2702.doc

www.scapa.com