

Technical Data Sheet



PRO2KSATIN

PRO2KSATIN Clear Coat Aerosol is a low-gloss finish with full 2K performance. With our proven can-in-can 2K hardener-activation system, they are engineered to deliver outstanding durability and consistent sheen control.

CODE - PRO2KSATIN



proxl.com
Visit our website
for more products



Technical Data

Technical Information

Size	400ml
Basis of binder	Acrylic Resin
Colour	Clear
Coverage	0.6 - 0.8m ²
Temperature resistance	to 120 °C
Pot Life	24 hrs at 20 - 25°C
VOC Directive	2004/42/B(e) (840)
VOC content	672g/lt
Storage stability	Store in a cool dry place in original container between -10°C & +25°C
Shelf Life	3 years in appropriate storage (-10°-25°C, relative air humidity of max. 60%)

Substrates

- Solvent or water based basecoat paint


Surface Preparation

- 1 Carry out test spray
- 2 Areas to be sprayed must be free of grease, dust and dry
- 3 For professional use only. Isocyanate training is required before use.
- 4 Wear an appropriate respirator (recommended type A2/P3)

Ready-to-use materials containing isocyanates can irritate the respiratory system and cause allergic reactions. There is a risk of sensitization with inhalation of vapours and spray mist. When dealing with substances containing isocyanates, you should observe all guidelines for using solvent-based coatings. Spray mist and vapours should NOT be inhaled. Allergy and asthma sufferers and people who are prone to respiratory diseases should not work with isocyanates materials.

Application Guide

- For optimal result, bring can to 20 - 25 °C and in a relative air humidity of 45 - 60%.
- Please note: a high air humidity can cause loss of gloss.
- Once activated, use within 24 hours.

	Remove cap from base.
	Insert metal ring into lug in the base of can.
	Pull ring fully down (10mm) and turn 360° to release the activator then shake for 2 mins <small>When stored at cool temperatures, the 2K Hi-Speed primer filler may also be used for several days following activation. Allow to heat to room temperature prior to use (approx. 20°).</small>
	Apply in cross coats from distance of 250mm from object.
	Apply 2-3 coats. Film thickness 50um.
	Allow 2 mins for flash off between coats.
	Infrared for 15-25 mins
	Dustr dry 5 mins @20°C Touch dry 5 hours Overcoatable 2 mins @20°C <small>The drying time depends on surrounding temperature, air humidity and thickness of the applied coat.</small>
	After use, turn aerosol upside down and empty valve

DISPOSAL

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed of as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.

ENVIRONMENTAL

ProXL is committed to use formulations without restricted or critical ingredients and to achieve the best possible performance. The caps and packagings are made of recyclable material.

ProXL is committed to use formulations without restricted or critical ingredients and to achieve the best possible performance. The caps and packagings are made of recyclable material.

DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of Alpha Coatings Limited trading as Capella Solutions Group's ("Capella") knowledge, however, you must satisfy yourselves that the Goods are suitable for your needs by way of your independent testing or other processes. Capella makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Capella assume liability arising out of the application or use of the Goods other than any liability which cannot be limited by law including but not limited to liability for: (a) death or personal injury caused by negligence; (b) fraud or fraudulent misrepresentation; and (c) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Capella's total liability shall not exceed the cost of the Goods. Capella's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise. It is the Customer's responsibility to ensure that the guidance on the Technical Data Sheet is followed.