

MOULDMASTER 20 TDS

RTV2 Silicone Rubber for Industrial use.

Bicomponent poly-condensation silicone indicated for mold making applications.

1- MAIN CHARACTERISTICS

Mouldmaster 20 is a poly-condensation curing, two component silicone that vulcanises at room temperature. It presents the following special features:

1. Medium Shore A hardness (Approx. 20)
2. High tear strength
3. Low dimensional variation

2- APPLICATIONS

Mouldmaster 20 is indicated for use in the following application:

1. Industrial (low dimensional variation, high mechanical resistance, long life of the mould)

3- PROCESSING

Before the casting of Epoxy, Polyester and PU resins of the silicone please apply a release agent to protect the silicone mould. If the resin is aggressive, apply it for each casting.

If you use for the first-time this silicone or a new resin, please do a small test before it does not compromise the work.

Take the two bi-component products supplied by Mouldlife (BASE and CATALYST NON FLAMMABLE CURING AGENT) and shake before use in order to homogenise each component prior to mixing. Base component is white, Mouldmaster catalyst non flammable curing agent is transparent/yellowish.

Mixing ratio must be 100:10 (10 units of catalyst for every 100 base units). For example, 1KG of base, add 100g of catalyst. This ratio must be respected to ensure the final characteristics of the product. DO NOT exceed the recommended ratio for the curing agent. You can use less catalyst (3-4%) than the recommended ratio (5%), in this case the dimensional change will be lower but setting time will increase.

The hardness is reached after a few hours (see table) and if the correct percentage of catalyst is respected. After 24 hours the product is cured. After 72 hours, perfectly hardened.

Mouldlife

MOULDING • CASTING • PROTOTYPING • SFX

Mix vigorously until the mixed white colour is homogeneous. Once the product is completely mixed, it is ready to be melted and it is recommended to pour the silicone from a height of 30CM into the mould.

Complete curing takes about 72 hours after mixing the two components. However, the product can be disassembled in just 18-24 hours.

The WT value in the table refers to a standard temperature of 23°C. The ST setting time is the time required for the silicone to harden from the start of mixing the two components. The ST shown in the table refers to a standard temperature of 23°C.

4- IMPORTANT RECOMMENDATIONS

Before handling the product, read the safety data sheet and make sure to get all the information required for safe use.

Test the product in a small scale quantity before extending the use in larger scale.

Condensation bases accelerate naturally near the expiration date; it is recommended to use, in this case, less catalyst so that the product acquires flexibility and withdrawal.

Before use, homogenize base and catalyst separately for possible sedimentation.

If necessary, use compressed air to facilitate this separation. Do not use any tools to force the separation of the model from the mould.

Working time and setting time are reduced if the temperature exceeds 23°C (e.g., if the temperature is 40°C, the working time and setting time are approximately cut in half). If the temperature is less than 23°C, the working time and setting time increase considerably.

5- Physical and Chemical Characteristics

The figures provided are only intended as a guide and should not be used in preparing specifications.

Component BASE (uncured)

Properties	Specifications	Analytical Method
Viscosity	<40000 cP	Internal Method (Brookfield)
Density (Metric System, 23°C/73°F)	1,22 g/cc	

Base + Catalyst (cured components)

Properties	Specifications	Analytical Method
Mixing Ratio	100:10	N/A
Working time/Pot life (23°C/73°F) *	50	Internal Method (Brookfield)
Setting time (23°C/73°F)	24 h	
Shore A hardness after 24 hours, 23°C	19 shA	ASTM D2240
Shore A hardness after 72 hours, 23°C	21 shA	ASTM D2240
Tensile Strength (Metric System, 23°C)	3 N/mm ²	ASTM D412
Tear strength Die B (Metric System, 23°C)	21 N/mm	ASTM D624
Elongation at break (23°C)	270%	ASTM D412
Dimensional Variation 48 hours	0,33%	
Dimensional Variation 7 days	0,43%	

*The working time “WT”, also known as “pot life”, is the recommended time period for mixing/vacuuming prior to casting. The reported WT shown in the table refers to a standard temperature of 23°C.

Cured silicone properties are guaranteed within temperatures ranging from a minimum temperature of -40°C to a maximum temperature of +200°C.

6- Shelf Life and Storage Conditions

The “Best use before end” date of each batch is shown on the product label.

12 months if stored correctly at a temperature between 5° and 27°C (41° - 80°F).

7- Notes

The advice provided as oral or written recommendations or through product use demonstrations are based on the company knowledge.

Use and applications of the product by the user are not subjected to companies monitoring or restrictions, therefore the final responsibility falls on the user.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, however, the properties required for the intended use must be checked out for quality assurance reasons. Please contact your Sales Area Manager for support.