

Classifications

EN ISO 17632-A	EN ISO 17632-B	AWS A5.20 / SFA-5.20
T 46 4 P M21 1 H5	T 49 3 T1-1M21A-H5	E71T-1M/T-9M/T-12M JH4
T 46 2 P C1 1 H5	T 49 3 T1-1C1A-H5	E71T-1C/T-9C/T-12C H4

Characteristics and typical fields of application

Seamless rutile flux cored wire for single- or multilayer welding of Carbon, Carbon-Manganese steels and similar types of steels including fine grain steels with Argon-CO₂ shielding gas or pure CO₂. Main features: excellent weldability in all positions with high performance welding speed, very low spatter losses, good bead appearance, fast freezing and easy to remove slag. This wire is especially suitable for ship building, structural steel work or wherever good bead appearance is required. D1.8 Seismic Supplement approved. The wire is CTOD tested at -10°C. (14°F). This product can be used in sour gas applications. (HIC tested acc. to NACE TM-0284). Test values for SSC are available upon request. Typical hydrogen value 2.5 – 3.5 ml/100g weld metal.

Base materials

S235JR-S355JR, S235JO-S355JO, S450JO, S235J2-S355J2, S275N-S460N, S275M-S460M, P235GH-P355GH, P275NL1-P460NL1, P215NL, P265NL, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE240
 ship building steels: AH32, AH36, AH40; DH32, DH36, DH40; EH32, EH36, EH40; FH32, FH36, FH40
 ASTM A 106 Gr. A, B, C; A 181 Gr. 60, 70; A 283 Gr. A, C; A 285 Gr. A, B, C; A 350 Gr. LF1; A 414 Gr. A, B, C, D, E, F, G; A 501 Gr. B; A 513 Gr. 1018; A 516 Gr. 55, 60, 65, 70; A 573 Gr. 58, 65, 70; A 588 Gr. A, B; A 633 Gr. C, E; A 662 Gr. B; A 711 Gr. 1013; A 841 Gr. A; API 5 L Gr. B, X42, X52, X56, X60, X65

Typical analysis

	Gas	C	Si	Mn
wt.-%	M21	0.06	0.40	1.45
wt.-%	C1	0.04	0.35	1.25

Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength R _e	Tensile strength R _m	Elongation A (L _e =5d ₀)	Impact energy ISO-V KV J			
	MPa	MPa	%	-20°C	-40°C	-46°C	-50°C
u	500 (≥ 460)	590 (530–620)	26 (≥ 22)	100 (≥ 47)	70 (≥ 47)	50 (≥ 27)	45 (≥ 27)
u1	470 (≥ 460)	560 (530–620)	28 (≥ 22)	80 (≥ 47)			
s1	510 (≥ 460)	590 (530–620)	26 (≥ 22)		80 (≥ 47)	41 (≥ 27)	

u untreated, as welded – shielding gas M21

u1 untreated, as welded – shielding gas C1

s1 stress relieved 620°C/1 hour - shielding gas M21

Operating data

	Polarity	DC+	Dimension mm
	Shielding gas	M21, C1	1.0
	(EN ISO 14175)		1.2
			1.4
			1.6

Welding with standard GMAW-facilities possible

Approvals

TÜV (06219), DB (42.052.03), DNV, ABS, LR, BV, RINA, RS, CWB, CE, D1.8 seismic supplement; MIL-DTL-24403/1F: MIL-71T-1C, MIL-71T-1M